

No. TD : P-204 Revision : 00 Effective Date : 08/09/2023

PROPAN PFW-333 is a special blend of waxes, available in natural color to protect and maintain the natural color of wood, give a good block resistance. **PROPAN PFW-333** is a solid paste formulation which make it pleasant and easy to use. Suitable for any types of wood and most interior application from furniture, handicrafts, to carvings and turnings.

PRODUCT SPECIFICATION

aint Specialist

Туре	: Waxes
Appearance	: Natural and colored paste
Solid content by weight	: 30 ± 1%
Flash point	: 23ºC
Packing	: 1 kg, 4 kg

APPLICATION

Application condition Application method Substrate Theoretical coverage : 25 - 35°C, 60 - 80%RH : Wipping : Kamper or other wood

 \therefore Namper of other wo

: 20 - 25 m²/kg depending on the absorbency of the wood

OTHERS

Shelf life: One year if stored in cool and dry condition in original sealed can.Storage and handling: Store in room temperature bellows 30°C.

SURFACE PREPARATION

- 1. The surface must be clean, dry, and free from oil.
- 2. Remove any dust by wiping with cloth.

APPLICATION INFORMATION

- 1. Apply thin coat of **PROPAN PFW-333** using a brush or soft, lint free cloth. Finish in the direction of the grain.
- 2. Allow drying for about 15 minutes.
- 3. Buff the wax along the wood grain using a clean soft, lint free cloth.
- 4. Apply second coat to achieved a higher gloss finish and offer added protection.

CARE AND MAINTENANCE

Subsequent coats of **PROPAN PFW-333** can be applied as required to maintain the finish. The use of other maintenance product such as aerosol polishes may result in some removal of **PROPAN PFW-333**.

SAFETY PRECAUTION

FIRST AID:

- Eyes : In the case of accidental splashes, flush eyes with water immediately and obtain medical advice
- Skin : Wash skin thoroughly with soap and water or approved industrial cleaner. Do not use solvent or thinners
- > Inhalation : Remove patient to fresh air area, loosen collar, and keep patient rested

Page 1 of 2

DISCLAIMER

S

This document contains information issued based on the best and latest of Propan's knowledge in accordance to laboratory testing and practical application experience. The end user must test the product's suitability for their specific application and purpose. Propan shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements. This document is subjected to change without further notice. Please consult Propan for any specific guidance on the suitability of this product for their needs or for any specific application practices.

PT. PROPAN RAYA I.C.C | Jl. Gatot Subroto KM. 8 Tangerang 15810, Indonesia P: +62 215930 3333 | F : +62 21 5924 694 | W : <u>www.propanraya.com</u> | E : info@propanraya.com