ULTRAN AQP-630

No. TD : A-026 Revision : 00 Effective Date : 11/03/2019

ULTRAN AQP-630 is a high quality politur based on Acrylic Emulsion resin which is designed to provide good flow, easy in application and good adhesion on substrate. This product is ideal for the protection and decoration of interior and exterior housing component. It shows the transparent and clear colors.

PRODUCT SPECIFICATION

Туре

: Acrylic Emulsion Resin

AQUA AQP-630	Appearance	Gloss Level (%)	Solid Content (NV, w/w)	Viscosity (30°C) sec	Specific Gravity
Colors	Colored liquid	50 - 60	37 ± 2 %	20 ± 5 (Din 6)	1.04 ± 0.02 g/cc

Color Flash Point Packing	 Brown Bamboo, Fresh Palisander, Yellow Bamboo N/A 1 It. in steel can 	Bamboo, Green Bamboo, Manggis, o
APPLICATION Application condition Application method Substrate Thinner Thinning ratio by volume Application viscosity (Din cup 4, 30°C) Pot life of mixture Coating Amount (wet) Theoretical coverage	 25 - 35°C, 60 - 80%RH Brush or air spray Kamper or other wood Water Water is used if necessary 55 ± 5 sec by brush or 18 ± N/A 60 - 80 g/m² of mixture per 12 - 14 m²/lt. at ca 80 g/m² 	± 2 sec by spray
FILM PROPERTIES Drying time Dust Free Tack Free Recoating time Adhesion on Kamper Resistance	 : 10 - 15 minutes : 30 - 40 minutes : wet on dry = after 60 - 90 n : GT = 0 - 1 • Water : Good • Weather : Good • QUV 500 hours : Good 	 d Blocking 2 Psi : N/A d Hot and Cold Check : N/A

: Good

- QUV 500 hours
- Yellowing

OTHERS

Shelf life: Two years if stored in cool and dry condition in original sealed canStorage and handling: Store in good ventilation room temperature and mix before use

SURFACE PREPARATION

- I The surface must be clean, dry, and free from oil.
- Remove oil, grease, or dirt with solvent or appropriate method (wire brush, steel wool, or sand paper no. 120 - 150 for Oak wood, no. 150 - 180 for Rubber and Ramin wood, and no. 180 followed by 240 for Cherry wood).

APPLICATION INFORMATION

- Mix one part of **ULTRAN AQP-630** before use.
- Spray even coat of **ULTRAN AQP-630** at coating amount 80 100 g/m².
- Sand the surface with sandpaper no. 280 or 400 after drying 2 3 hours.
- Good ventilation in working area is suggested.

RECOMMENDED COATING SYSTEM

No.	APPLICATION STEP	PRODUCT	REC. COATING
1.	Base coat	ULTRAN AQP-630	1 x
2.	Top coat	ULTRAN AQP-630	1 x

SAFETY PRECAUTION

This product is non toxic. It does not contain any material with mercury or heavy metals. Avoid contact with the skin and eyes. Wear suitable protective clothing such as goggles, dust masks, and gloves. Use barrier cream.

This product is non flammable.

FIRST AID:

- Eye contact : Rinse immediately with plenty of water for at least 15 minutes; seek medical advice
 - Skin contact : Wash with soap and water. If irritation occurs, seek medical advice
 - Ingestion : Provide symptomatic treatment and seek medical advice
- Inhalation : Remove person to fresh air. Keep patient rested and give artificial respiration