# S-KOTE Pelindung Dinding Batu Alam

int Specialist

No. TD : S-021 Revision : 00 Effective date : 15/04/2024

# **PRODUCT DESCRIPTION**

**S-KOTE** is a natural stone coating which is made from solvent based acrylic with clear and colored appearance. It provides maximum protection to the surface of natural stone and brick and gives clear or uniform color to the surface so that it becomes more beautiful and artistic. This quality provides good adhesion to the substrate, fungus resistant, good weather resistance and suitable for indoor or outdoor uses.

PRODUCT DATA Type Appearance Color Finish Solid by volume Specific gravity Theoretical coverage Flash point Drying time Packaging Storage and handling	<ul> <li>Solvent based acrylic</li> <li>Liquid</li> <li>Clear, black, red brick and as shown in the color card</li> <li>Gloss and Dof</li> <li>25 - 30 %</li> <li>0.90 - 0.95</li> <li>6 - 10 m²/litre (1 coat, depend on the substrate absorption)</li> <li>32° C</li> <li>2 hours (30°C)</li> <li>0.9 litres</li> <li>Store in cool and dry condition in original unopened packaging. Protect from dampness and direct sunlight. Mix before use.</li> </ul>
APPLICATION Thinning ratio by volume Application method Substrate Recommended dry film thickness Recoating interval Thinner/clean up Cleaning	<ul> <li>: - (ready to use)</li> <li>- For wet look appearance, S-KOTE SC-52 SB Clear Gloss can be diluted up to 100%</li> <li>: Brush</li> <li>: Natural stone, brick</li> <li>: 60 microns (2 – 3 coats)</li> <li>: Minimum 2 hours ( 30°C ), when the first film already dry Maximum –</li> <li>: Thinner serbaguna</li> <li>: Wash all equipment immediately after use with thinner</li> </ul>

#### SURFACE PREPARATION

- The surface must be clean, dry, sound and free from all contaminants.
- Remove all loose material by thorough brushing and scraping using active fibre brush.
- Treat any areas affected by mold, algae, moss and lichens with PROPAN FUNGICIDAL WASH

# APPLICATION CONDITION

Temperature: Minimum 25°C<br/>Maximum 35°CHumidity maximum: 80 % RHProvide adequate ventilation during application and drying.

Page 1 of 2

PT. PROPAN RAYA I.C.C | Jl. Gatot Subroto KM. 8 Tangerang 15810, Indonesia P: +62 215930 3333 | F : +62 21 5924 694 | W : www.propanraya.com | E : info@propanraya.com

## **RECOMMENDED COATING SCHEDULE**

int Specialist

- Preceding coats
- Subsequent coats
- : S-KOTE, 1 coat : S-KOTE, 1 - 2 coat

## SAFETY PRECAUTIONS

S-KOTE is flammable and does not contain heavy metals in its materials such as lead. Avoid contact with skin and eyes. Do not inhaled. Wear suitable protective equipment such as googles, dust mask and gloves. For more information refer to material safety data sheet.

#### First Aid

1 11 01 7 110		
Skin contact	:	Wash with soap and water. If irritation occurs, seek medical advice
Eye contact	:	Rinse immediately with plenty of water. Seek medical advice if irritation persists.
Inhalation	:	Take the person out to get more fresh air, loosen collar and avoid exertion. Keep
		patient rested and help using breathing apparatus.

#### Disclaimer

This document contains information issued based on the best and latest of Propan's knowledge in accordance to laboratory testing and practical application experience. The end user must test the product's suitability for their specific application and purpose. Propan shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements. This document is subjected to change without further notice. Please consult Propan for any specific guidance on the suitability of this product for their needs or for any specific application practices.