

PROCRYL DTM ARP-20760

No. TD : A-037
Revision : 05
Effective Date : 22/02/2024

PRODUCT DESCRIPTION & USES

PROCRYL DTM ARP-20760 is a one component paint based on special modified acrylic resin with good weather resistance and mechanical properties. This product is suitable for general metal substrate and can be applied to the metal substrate without any primer (Direct to Metal).

FEATURE

- Direct to Metal Application
- Surface Tolerant
- Good Corrosion Resistance
- Good Adhesion, Hardness and Flexibility
- Good Weather Resistance
- Easy to Apply and Fast Dry

PRODUCT SPECIFICATION

Colours : Black, Grey, Red Oxide and others color as request
Finish : Doff – Satin
Volume Solid : $50 \pm 2 \%$
Specific Gravity : 1.15 ± 0.04 g/cc
Flash Point : 23 °C
Packaging : 5 & 20 Liters
Storage Stability : 24 Months. If it is stored in cool and dry place, also in its original not opened package

APPLICATION

Instruction for Use : Stir well before use, preferable by means use mechanical mixer to ensure good homogeneity
Application Condition : 25 – 35 °C, 60 – 80% RH
Application Method : Airless Spray Air Spray Brush/Roller
Thinning Ratio by Volume : 5 – 20 % 20 – 30 % 5 – 10 %
Thinner : THSG-90300, THSG-90310, THSG-90320, Thinner Yori Hitam
Tip Size for Airless Spray Gun : 0.013 – 0.015 inch Air pressure : approx. 150 bar; 2100 psi
Nozzle Orifice for Air Spray : 1 – 1.5 mm Air pressure : approx. 3 - 4 bar; 40 - 60 psi
Wet Film Thickness (WFT) : 60 – 80 microns or 2.4 – 3.2 mills
Dry Film Thickness (DFT) : 30 – 40 microns or 1.2 – 1.6 mills
Theoretical Coverage : 12.5 m² /liter (DFT = 40 microns)

FILM PROPERTIES

Drying Time (@ DFT = 40 mic)	:	20°C	30°C	40°C
• Surface Dry	:	5 – 7 minutes	4 – 5 minutes	3 – 4 minutes
• Hard Dry	:	60 – 90 minutes	45 – 75 minutes	30 – 60 minutes

Re-coating interval : Minimum 20 minutes (30°C)*
Maximum — *

Provide adequate ventilation during application and drying.

*It is depends on weather, exposure, thickness, storage.

*For more details please contact PROPAN Technical supervisor

RECOMMENDED COATING SYSTEM

Primer Coat	: PROCRYL DTM ARP-20760
Finish Coat	: PROCRYL DTM ARC-50760, PROTHANE DTM PUT-50891
Recommended Dry Film Thickness	: 1 coat (40 microns / coat)

SURFACE PREPARATION

1. All surfaces should be clean, dry and free from contamination accordance with SSPC-SP 1 solvent cleaning.
2. Oil or grease should be removed by solvent cleaning or industrial detergent.
3. Blast cleaning with suitable blasting material minimum Sa2, hand or power tool cleaning to a minimum standard of St2 in accordance with the ISO 8501-1 : 1988 or SSPC-SP 2.
4. Provide adequate ventilation during application.

INSTRUCTION FOR USE

Firstly stir well **ARP-20760** until homogeneous, add thinner if needed and mix thoroughly. Mixed material could apply using airless spray, air spray, brush or roller. Use Thinner **THSG-90300**, **THSG-90310**, **THSG-90320** and **Thinner Yori Hitam** as solvent cleaner. Provide adequate ventilation during application and drying.

SAFETY PRECAUTION

Avoid contact with the skin and eyes. Wear suitable protective coating, such as overalls, goggles, dust mask, and gloves. Use barrier cream. Provide adequate ventilation during application. Do not breathe vapor of spray. This product is flammable. Do not smoke. Use only explosion proof equipment.

FIRST AID:

- | | |
|------------|--|
| General | : In all cases of doubt, or when symptoms persist, seek medical attention. Never give anything by mouth to an unconscious person. |
| Eyes | : In the case of accidental splashes, flush eyes with clear running water for 5 minutes while holding eyelids open. If irritation persist, seek medical attention. |
| Skin | : Wash off thoroughly with plenty of water and soap. Do not use solvent or thinner. Removed contaminated clothing. If irritation persist, seek medical attention. |
| Inhalation | : Remove affected person to fresh air area, loosen collar, provide oxygen if breathing is difficult. If affected person is not breathing, administer CPR and seek emergency medical attention. |

DISCLAIMER

This document contains information issued based on the best and latest of Propan's knowledge in accordance to laboratory testing and practical application experience. The end user must test the product's suitability for their specific application and purpose. Propan shall not be liable for defects where the application of the Product has not been made fully in accordance with the recommendations and requirements. This document is subjected to change without further notice. Please consult Propan for any specific guidance on the suitability of this product for their needs or for any specific application practices.